

OM2 (50/125μm) Multimode Fibre

OM2(50/125μm)多模光纤



Description 产品描述

OM2 (50/125μm) Bend Insensitive Multimode Fibre complies with or exceeds ISO/IEC 11801-1 OM2 specification, IEC 60793-2-10 A1-OM2 specification, and TIA-492AAAF A1-OM2 specification.

OM2 (50/125μm) 弯曲不敏感多模光纤符合或超过 ISO/IEC 11801-1 OM2 规范、IEC 60793-2-10 A1-OM2 规范和 TIA-492AAAF A1-OM2 规范。

Features 特点

- Superior geometry uniformity
优越的几何均匀性
- Low attenuation
低衰减
- High bandwidth at wavelengths of 850nm and 1300nm
850nm 和 1300nm 波长的高带宽
- Manufactured by PCVD process
PCVD 工艺制造
- Extremely refined refractive index profile
极其精细的折射率分布
- Very low macro-bending sensitivity
极低的宏弯灵敏度
- Coated with dual layer UV curable acrylate
涂有双层紫外线固化丙烯酸酯

Benefits and Applications 优势和应用

- Local area networks (LAN)
局域网 (LAN)
- Video, voice and data services
视频、语音和数据服务
- Gigabit Ethernet using laser or LED light sources
使用激光或 LED 光源的千兆以太网
- supports the use and installation of optical cables with a small bending radius
支持小弯曲半径光缆的使用和安装
- High resistance to micro-bending
高抗微弯性
- Optimized performance in tight-buffer cable applications
紧缓冲电缆应用中的优化性能
- Stable performance over a wide range of environmental conditions
在广泛的环境条件下性能稳定

Specifications 参数

Geometrical Characteristics 几何特性

Characteristics 特性	Specified values 数据	Units 单位
Core Diameter 芯直径	50±2.5	[μm]
Core Non-Circularity 芯不圆度	≤5.0	[%]
Cladding Diameter 包层直径	125.0±1.0	[μm]
Cladding Non-Circularity 包层不圆度	≤1.0	[%]
Coating Diameter 涂层直径	245±7	[μm]
Coating-Cladding Concentricity Error 涂层/包层同心度误差	≤10.0	[μm]
Coating Non-Circularity 涂层不圆度	≤6.0	[%]
Core-Cladding Concentricity Error 芯/包层同心度误差	≤1.5	[μm]
Delivery Length 交货长度	up to 17.6	[km/reel]

Optical Characteristics 光学特性

Characteristics 特性	Conditions 条件	Specified values 数据	Units 单位
Attenuation 衰减	850nm	≤2.3	[dB/km]
	1300nm	≤0.6	[dB/km]
Overfilled Modal Bandwidth 满注入带宽	850nm	≥500	[Mhz·km]
	1300nm	≥500	[Mhz·km]
Numerical Aperture 数值孔径		0.200±0.015	--
Group Refractive Index 群折射率	850nm	1.482	--
	1300nm	1.477	--
Zero Dispersion Wavelength(λ ₀) 零色散波长(λ ₀)		1295-1340	[nm]
Zero Dispersion Slope(S ₀) 零色散斜率(S ₀)	1295nm≤λ ₀ ≤1310nm	≤0.105	[ps/(nm ² ·km)]
	1310nm≤λ ₀ ≤1340nm	≤0.000375(1590-λ ₀)	[ps/(nm ² ·km)]
Macrobending Loss 宏弯损耗	2 Turns @ 15 mm Radius 2圈, 半径15mm	850nm ≤0.1	[dB]
	2 Turns @ 15 mm Radius 2圈, 半径15mm	1300nm ≤0.3	[dB]
	2 Turns @ 7.5 mm Radius 2圈, 半径7.5mm	850nm ≤0.2	[dB]
	2 Turns @ 7.5 mm Radius 100圈, 半径37.5mm	1300nm ≤0.5	[dB]

Backscatter Characteristics 背向散射特性 (1300nm)

Characteristics 特性	Specified values 数据	Units 单位
Step (Mean of Bidirectional Measurement) 台阶 (双向测量的平均值)	≤0.10	[dB]
Irregularities Over Fibre Length and Point Discontinuity 长度方向的不规律性和点不连续性	≤0.10	[dB]
Attenuation Uniformity 衰减不均匀性	≤0.08	[dB/km]

Environmental Characteristics 环境特性 (850nm & 1300nm)

Characteristics 特性	Conditions 条件	Specified values 数据	Units 单位
Temperature Cycling 温度循环附加衰减	-60°C to +85°C	≤0.10	[dB/km]
Temperature-Humidity Cycling 温度-湿度循环附加衰减	-10°C to 85°C, 4% to 98% RH -10°C 到 85°C, 4% 到 98% 相对湿度	≤0.10	[dB/km]
Water Immersion 浸水附加衰减	23°C, 30 days 23°C, 30天	≤0.10	[dB/km]
Dry Heat 干热附加衰减	85°C, 30 days 85°C, 30天	≤0.10	[dB/km]
Damp Heat 湿热附加衰减	85°C, 85% RH, 30 days 85°C和85%相对湿度, 30天	≤0.10	[dB/km]

Mechanical Specifications 机械特性

Characteristics 特性	Conditions 条件	Specified values 数据	Units 单位
Proof Test 筛选张力	--	≥9.0	[N]
	--	≤1.0	[%]
Coating Strip Force 涂层剥离力	typical average force 典型平均值	≥100	[kpsi]
	peak force 峰值	1.5	[N]
Dynamic Stress Corrosion Susceptibility Parameter (nd, typical) 动态疲劳参数 (nd, 典型值)		≥1.3, ≤8.9	[N]
		20	--